

Vám přináší **StreetMark**



Termoplastické značení

Testování StreetMark na EN71-3 a PAH

Termoplastické značení StreetMark

Shrnutí výsledků:

-Těžké kovy (EN 71-3): vše v pořádku. Žádný výskyt těžkých kovů nebo podobných látek.

- PAH: také vše v pořádku. Žádný výskyt polycyklických aromatických uhlovodíků.

Testování probíhalo u německé laboratoři Veritas na přítomnost těžkých kovů (dle EN 71-3) a polycyklických aromatických uhlovodíků (PAH). Výsledky viz. níže.

Detailní výpis z testování: (v eng)



Test Report

Customer: 4soft, s.r.o.
Krkonoška 625
46841 Tanvald
Czech Republic

Contact Person: Mr. Dusan Smid

BV Order No.: -
Report No.: (25425)139-604574
Report Version: 1

Report Date: 19.05.2025

Sample Information

Testing Requirements: Tested according to "ordered" requirements

Sample Description: Termoplasticky material StreetMark

Sample Reception: 12.05.2025

Performance Date: 12.05.2025 - 19.05.2025


Sampled By: client

Material: Thermoplastic
Colour: grey
Country of Origin: Czech Republic

Country of Dest.: International

Submitted Samples

No. 1



Termoplastické značení StreetMark

Deutsche
Akkreditierungsstelle
D-PL-12024-02-00

Report No.: (25425)139-604574

Summary of Test Results

Tested according to "ordered" requirements

Tests required	Evaluation	Remark
Heavy metals, migration of certain elements - scraped off toy material	Pass	
PAH (Polycyclic aromatic hydrocarbons)	Pass	

Deutsche
Akkreditierungsstelle
D-PL-12024-02-00

Report No.: (25425)139-604574

Tested Samples

Article No	Sample ID	Sample description	
	604574-01	1) Plastic sample grey	

Bureau Veritas Consumer Products Services Germany GmbH
www.bureauveritas.de/cps
Phone: +49 (0)40 - 740 41 - 0Managing Director: Joerg-Timm Kilsch
VAT-No.: DE164793120
Reg.No.: Schwerin HRB 3564

TEMP-0029-DEU-CQN-V03 / RPRT-0033-SW-V03

Schwerin
Mettener Straße 12-14, 19061 Schwerin
cps-schwerin@bureauveritas.comHamburg
Oehlecker Ring 40, 22419 Hamburg
cps-hamburg@bureauveritas.comTürkheim
Businesspark A96, 86842 Türkheim
cps-tuerkheim@bureauveritas.comNuremberg
Thurn-und-Taxis-Str. 18, 90411 Nuremberg
cps-nuernberg@bureauveritas.com

3 / 6

Termoplastické značení StreetMark



Deutsche
Akkreditierungsstelle
D-PL-12024-02-00

Report No.: (25425)139-604574

Test Results

Tested according to "ordered" requirements

Sample Description: 1) Plastic sample grey		Lab Reference No: 604574-01	
Test Method / Standard: Determination of PAH (Category 2, other consumer products): AFPS GS 2019:01 PAK: GS-specification 2019-05, ultrasound extraction with Toluene, GC-MS analysis, reporting limit: 0.2 mg/kg			
Test Location & Accreditation: Parameter has been analyzed at accredited BVCPs laboratory Schwerin.			
Parameter	Limit	Value	Evaluation
Benzo (a) pyrene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Benzo (e) pyrene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Benzo (a) anthracene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Benzo (b) fluoranthene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Benzo (j) fluoranthene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Benzo (k) fluoranthene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Chrysene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Dibenzo (a,h) anthracene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Benzo (g,h,i) perylene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Indeno (1,2,3-cd) pyrene	≤ 0.5 mg/kg	<0.2 mg/kg	Pass
Phenanthrene		<0.2 mg/kg	No Specification
Pyrene		<0.2 mg/kg	No Specification
Anthracene		0.34 mg/kg	No Specification
Fluoranthene		<0.2 mg/kg	No Specification
Sum of Phenanthrene, Pyrene, Anthracene and Fluoranthene	≤ 10 mg/kg	0.34 mg/kg	Pass
Naphthalene	≤ 2 mg/kg	<0.2 mg/kg	Pass
Sum of all listed PAH's	≤ 10 mg/kg	0.34 mg/kg	Pass
Test Method / Standard: Heavy metals, migration of certain elements - scraped off toy material: EN 71-3:2019+A2:2024, reporting limits: Cr III / Cr VI: 0.05 mg/kg, Hg / organic tin: 0.1 mg/kg, As / Ba / Cd / Co / Mn / Ni / Pb / Sb / Se / Sn / Sr: 1 mg/kg, Al / B / Cu / Zn: 10 mg/kg; special case: Hg: 0.02 mg/kg			
Test Location & Accreditation: Parameter has been analyzed at accredited BVCPs laboratory Schwerin.			
Parameter	Limit	Value	Evaluation
Aluminium (Al)	≤ 28130 mg/kg	<10 mg/kg	Pass
Antimony (Sb)	≤ 560 mg/kg	<1 mg/kg	Pass
Arsenic (As)	≤ 47 mg/kg	<1 mg/kg	Pass
Barium (Ba)	≤ 18750 mg/kg	<1 mg/kg	Pass
Boron (B)	≤ 15000 mg/kg	<10 mg/kg	Pass
Cadmium (Cd)	≤ 17 mg/kg	<1 mg/kg	Pass
Chromium (Cr)	≤ 460 mg/kg	0.0752 mg/kg	Pass
Chromium III	≤ 460 mg/kg	0.0752 mg/kg	Pass
Chromium VI	≤ 0.053 mg/kg	<0.02 mg/kg	Pass
Cobalt (Co)	≤ 130 mg/kg	<1 mg/kg	Pass
Copper (Cu)	≤ 7700 mg/kg	<10 mg/kg	Pass
Lead (Pb)	≤ 23 mg/kg	<1 mg/kg	Pass
Manganese (Mn)	≤ 15000 mg/kg	<1 mg/kg	Pass
Mercury (Hg)	≤ 94 mg/kg	<0.1 mg/kg	Pass
Nickel (Ni)	≤ 930 mg/kg	<1 mg/kg	Pass
Organic tin	≤ 12 mg/kg	Test not necessary	-

Bureau Veritas Consumer Products Services Germany GmbH
www.bureauveritas.de/cps
Phone: +49 (0)40 - 740 41 - 0

Managing Director: Joerg-Timm Killisch
VAT-No.: DE164793120
Reg.No.: Schwerin HRB 3564

Schwerin
Mettener Straße 12-14, 19061 Schwerin
cps-schwerin@bureauveritas.com

Hamburg
Oehleckerweg 40, 22419 Hamburg
cps-hamburg@bureauveritas.com

Türkheim
Businesspark A96, 86842 Türkheim
cps-tuerkheim@bureauveritas.com

Nuremberg
Thurn-und-Taxis-Str. 18, 90411 Nuremberg
cps-nuremberg@bureauveritas.com

TEMP-0029-DEU-CON-V03 / RPRT-0033-SW-V03

4 / 6

Termoplastické značení StreetMark

Deutsche
Akkreditierungsstelle
D-PL-12024-02-00

Report No.: (25425)139-604574

Sample Description:	1) Plastic sample grey			Lab Reference No:	604574-01
Test Method / Standard:	Heavy metals, migration of certain elements - scraped off toy material: EN 71-3:2019+A2:2024, reporting limits: Cr III / Cr VI: 0.05 mg/kg, Hg / organic tin: 0.1 mg/kg, As / Ba / Cd / Co / Mn / Ni / Pb / Sb / Se / Sn / Sr: 1 mg/kg, Al / B / Cu / Zn: 10 mg/kg; special case: Hg: 0.02 mg/kg				
Test Location & Accreditation:	Parameter has been analyzed at accredited BVCPs laboratory Schwerin.				
Parameter	Limit	Value	Evaluation		
Selenium (Se)	≤ 460 mg/kg	<5 mg/kg	Pass		
Strontium (Sr)	≤ 56000 mg/kg	2.45 mg/kg	Pass		
Tin (Sn)	≤ 180000 mg/kg	<1 mg/kg	Pass		
Zinc (Zn)	≤ 46000 mg/kg	<10 mg/kg	Pass		

The test results relate only to the received and tested item. Without the written consent of Bureau Veritas Consumer Products Services Germany GmbH excerpts of this report shall not be reproduced. If the standard or the customer defines no decision rule, the laboratory applies a decision rule following the "Binary Statement for Simple Acceptance Rule (w=0)" (chapter 4.2.1) of ILAC Guidelines on Decision Rules and Statements of Conformity (ILAC-G8:09/2019). The results in this test report are reported in a simplified way (et al. without measurement uncertainty).

The measurement uncertainties underlying each procedure can be viewed [here](#).

The testing of mixed samples is carried out at the customer's explicit request and may imply a deviation from the testing standard. Please note the following: results that are above the limit for the composite sample may be below the limit if the individual samples contained in the composite sample are tested separately. In these cases separate testing of the samples is recommended.



Stefan Pasedag

No results printed beyond this point in the report

Bureau Veritas Consumer Products Services Germany GmbH
www.bureauveritas.de/cps
Phone: +49 (0)40 - 740 41 - 0

Managing Director: Joerg-Timm Kilisch
VAT-No.: DE164793120
Reg No.: Schwerin HRB 3564

Schwerin
Mettener Straße 12-14, 19061 Schwerin
cps-schwerin@bureauveritas.com

Hamburg
Oehlbeckerring 40, 22419 Hamburg
cps-hamburg@bureauveritas.com

Tuerkheim
Businesspark A96, 86842 Tuerkheim
cps-tuerkheim@bureauveritas.com

Nuremberg
Thurn-und-Taxis-Str. 18, 90411 Nuremberg
cps-nuernberg@bureauveritas.com

TEMP-0028-CEU-CON-V03 / RPRT-0033-SW-V05

5 / 6

Termoplastické značení StreetMark



Report No.: (25425)139-604574

Parameters & CAS No.

Heavy metals, migration of certain elements - scraped off toy material	(CAS No.)
Aluminium (Al) (7429-90-5)	
Lead (Pb) (7439-92-1)	
Manganese (Mn) (7439-96-5)	
Mercury (Hg) (7439-97-6)	
Nickel (Ni) (7440-02-0)	
Strontium (Sr) (7440-24-6)	
Tin (Sn) (7440-31-5)	
Antimony (Sb) (7440-36-0)	
Arsenic (As) (7440-38-2)	
Barium (Ba) (7440-39-3)	
Boron (B) (7440-42-8)	
Cadmium (Cd) (7440-43-9)	
Chromium (Cr) (7440-47-3)	
Cobalt (Co) (7440-48-4)	
Copper (Cu) (7440-50-8)	
Zinc (Zn) (7440-66-6)	
Selenium (Se) (7782-49-2)	

Determination of PAH (Category 2, other consumer products)	(CAS No.)
Anthracene (120-12-7)	
Pyrene (129-00-0)	
Benzo (g,h,i) perylene (191-24-2)	
Benzo (e) pyrene (192-97-2)	
Indeno (1,2,3-cd) pyrene (193-39-5)	
Benzo (j) fluoranthene (205-82-3)	
Benzo (b) fluoranthene (205-99-2)	
Fluoranthene (206-44-0)	
Benzo (k) fluoranthene (207-08-9)	
Chrysene (218-01-9)	
Benzo (a) pyrene (50-32-8)	
Dibenzo (a,h) anthracene (53-70-3)	
Benzo (a) anthracene (56-55-3)	
Phenanthrene (85-01-8)	
Naphthalene (91-20-3)	

List s testováním povrchu Streetmark byl vytvořen 19.5.2025

Vypracoval: Mgr. Dušan Šmíd